

twinsealer 3700X

H2596-xxxx-1E

Trägergewebe base fabric	(DIN EN ISO 2076)	Markenpolyester trade mark polyester
Gewebeaufbau fabric structure		zweilagig, monofilament two layer, monofilament
Beschichtungsmaterial coating material		PVC
Flächengewicht total weight	(DIN EN ISO 2286-2)	ca. 3700 g/m² approx. 109 oz/yd ²
Dicke thickness	(DIN EN ISO 2286-3)	ca. 3 mm approx. 118 mm-inch
Höchstzugkraft (Kette/Schuss) tensile strength (warp/weft)	(DIN EN ISO 1421-1)	7800/4700 N/5cm 891/537 lbf/inch
Weiterreißfestigkeit (Kette/Schuss) tear resistance (warp/weft)	(DIN 53363)	1000/650 N 225/146 lbf
Schweißnahthaftung, Hochfrequenz welding adhesion, high frequency	(IVK 3.13)	100 N/5cm 11 lbf/inch
Kältebeständigkeit cold resistance	(DIN EN 1876-1)	- 30 °C - 22 °F
Brennverhalten flame resistance	(DIN 75200)	max. 100 mm/min. max. 100 mm/min.
Einsatzmöglichkeit possible application		z. B. Torabdichtung e.g. door sealings